

Type	Top Surface		Drive Surface		Max. width [mm]	Overall thickness aR [mm]	Tensile strength [N/mm]	Tractive force 1 % elongation FZ1% [N/mm]	Min. Pulley diameter dmin [mm]	Working temperatures				Final bonding		
	colour	colour	colour	colour						Permanent min. °C	max. °C	Short-termed min. °C	max. °C	Adhesive type	Pressing time min.	Pressing temp. °C
3-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	1,9	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	2,1	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
5-XR1	Rubber textured	T.Green	Rubber textured	Yellow	500	2,5	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
7-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	2,4	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
7-XR1	Rubber textured	T.Green	Rubber textured	Yellow	500	2,7	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10XR	Rubber textured	T.Green	Rubber textured	Yellow	500	2,6	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
10-XR1	Rubber textured	T.Green	Rubber textured	Yellow	500	3,0	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
15-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	3,0	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
15-XR1	Rubber textured	T.Green	Rubber textured	Yellow	500	4,0	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	3,8	900	20,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-XR	Rubber textured	T.Green	Rubber textured	Yellow	500	4,8	1350	30,0	320	-20	100	-30	130	FX+FXS	50	90-120
3-XP	Rubber textured	A.Green	Rubber textured	Orange	500	1,6	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-XP	Rubber textured	A.Green	Rubber textured	Orange	500	1,8	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
7-XP	Rubber textured	A.Green	Rubber textured	Orange	500	2,0	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10-XP	Rubber textured	A.Green	Rubber textured	Orange	500	2,4	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
2-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	1,4	90	3,0	15	-20	100	-30	130	FX+FXS	20	90-120
3-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	1,5	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	1,7	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
7-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	1,9	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	2,3	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
15-GREX	Rubber Smooth	Grey	Rubber Smooth	Grey	500	2,8	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
5-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	2,3	225	5,0	30	-20	100	-30	130	FX+FXS	30	90-120
7-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	2,5	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	2,8	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
15-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	3,3	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	3,8	900	20,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-AXR	Carbon Fabric	Black	Rubber Groove	Black	500	4,8	1350	30,0	320	-20	100	-30	130	FX+FXS	50	90-120
5-NOS	Rubber textured	Black	Rubber Dotted	A.Green	500	3,0	225	5,0	30	-20	100	-30	130	FX+FXS	30	90-120
7-NOS	Rubber textured	Black	Rubber Dotted	A.Green	500	3,2	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10-NOS	Rubber textured	Black	Rubber Dotted	A.Green	500	3,5	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120