



Type	Top Surface		Drive Surface		Max. width [mm]	Overall thickness aR [mm]	Tensile strength [N/mm]	Tractive force 1 % elongation FZ1% [N/mm]	Min. Pulley diameter dmin [mm]	Working temperatures				Final bonding		
	colour	colour	colour	colour						Permanent min. °C	Permanent max. °C	Short-termed min. °C	Short-termed max. °C	Adhesive type	Pressing time min.	Pressing temp. °C
1-ST	Rubber Smooth	T.Green	Cotton Fabric	Beige	500	0,7	54	1,5	10	-20	100	-30	130	FX+FXS	10	90-120
2-ST	Rubber Smooth	T.Green	Cotton Fabric	Beige	500	0,9	90	2,5	15	-20	100	-30	130	FX+FXS	10	90-120
3-GP/MOS	Rubber textured	M.Green	Carbon Fabric	Black	500	1,4	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-GP/MOS	Rubber textured	M.Green	Carbon Fabric	Black	500	1,6	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
2-FS	Rubber Smooth	T.Green	Carbon Fabric	Black	500	1,1	90	2,5	15	-20	100	-30	130	FX+FXS	20	90-120
3-FS	Rubber Smooth	T.Green	Carbon Fabric	Black	500	1,2	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
2-GS	Rubber Smooth	Grey	Carbon Fabric	Black	500	1,2	90	2,5	15	-20	100	-30	130	FX+FXS	20	90-120
3-GS	Rubber Smooth	Grey	Carbon Fabric	Black	500	1,3	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-GS	Rubber Smooth	Grey	Carbon Fabric	Black	500	1,5	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
2-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	1,2	90	2,5	15	-20	100	-30	130	FX+FXS	20	90-120
3-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	1,4	135	4,0	20	-20	100	-30	130	FX+FXS	20	90-120
5-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	1,6	225	5,0	25	-20	100	-30	130	FX+FXS	30	90-120
7-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	1,8	315	8,0	50	-20	100	-30	130	FX+FXS	30	90-120
10-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	2,1	450	10,5	70	-20	100	-30	130	FX+FXS	40	90-120
15-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	2,6	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	3,2	900	20,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	4,2	1350	30,0	320	-20	100	-30	130	FX+FXS	50	90-120
40-GP	Rubber textured	T.Green	Carbon Fabric	Black	500	5,5	1800	40,0	560	-20	100	-30	130	FX+FXS	50	90-120
2-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	0,9	90	2,5	15	-20	100	-30	130	FX	10	90-120
3-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	1,0	135	4,0	20	-20	100	-30	130	FX	10	90-120
5-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	1,2	225	5,0	25	-20	100	-30	130	FX	20	90-120
7-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	1,5	315	8,0	50	-20	100	-30	130	FX	20	90-120
10-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	1,8	450	10,5	70	-20	100	-30	130	FX	30	90-120
15-SU	Carbon Fabric	Black	Carbon Fabric	Black	500	2,3	675	15,0	125	-20	100	-30	130	FX	35	90-120
T-02	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	1,0	135	4,0	15	-20	100	-30	130	FX	10	90-120
T-05	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	1,2	225	5,0	25	-20	100	-30	130	FX	20	90-120
T-07	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	1,5	315	8,0	50	-20	100	-30	130	FX	20	90-120
T-10	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	1,8	450	10,5	70	-20	100	-30	130	FX	30	90-120
T-15	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	2,3	675	15,0	125	-20	100	-30	130	FX	35	90-120
T-20	Polyamid Fabric	D.Green	Polyamid Fabric	D.Green	500	3,1	900	20,0	250	-20	100	-30	130	FX	40	90-120