

Type	Top Surface		Drive Surface		Max. width [mm]	Overall thickness aR [mm]	Tensile strength [N/mm]	Tractive force 1 % elongation FZ1% [N/mm]	Min. Pulley diameter dmin [mm]	Working temperatures				Final bonding		
	colour	colour	Permanent min. °C	Permanent max. °C						Short-termed min. °C	Short-termed max. °C	Adhesive type	Pressing time min.	Pressing temp. °C		
3-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	2,5	135	4,0	30	-20	100	-30	130	FX+FXS	20	90-120
5-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	2,6	225	5,0	30	-20	100	-30	130	FX+FXS	30	90-120
7-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	2,9	315	8,0	60	-20	100	-30	130	FX+FXS	30	90-120
10-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	3,2	450	10,5	90	-20	100	-30	130	FX+FXS	40	90-120
15-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	3,6	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	4,3	900	22,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	5,4	1350	33,0	320	-20	100	-30	130	FX+FXS	50	90-120
40-CLT	Carbon Fabric	Black	Chrome leather	Grey	500	6,4	1800	44,0	560	-20	100	-30	130	FX+FXS	50	90-120
3-CLL	Chrome leather	Grey	Chrome leather	Grey	500	3,9	135	4,0	30	-20	100	-30	130	FX+FXS	20	90-120
5-CLL	Chrome leather	Grey	Chrome leather	Grey	500	4,0	225	5,0	30	-20	100	-30	130	FX+FXS	30	90-120
7-CLL	Chrome leather	Grey	Chrome leather	Grey	500	4,3	315	8,0	60	-20	100	-30	130	FX+FXS	30	90-120
10-CLL	Chrome leather	Grey	Chrome leather	Grey	500	4,6	450	10,5	90	-20	100	-30	130	FX+FXS	40	90-120
15-CLL	Chrome leather	Grey	Chrome leather	Grey	500	5,0	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-CLL	Chrome leather	Grey	Chrome leather	Grey	500	5,7	900	22,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-CLL	Chrome leather	Grey	Chrome leather	Grey	500	6,8	1350	33,0	320	-20	100	-30	130	FX+FXS	50	90-120
40-CLL	Chrome leather	Grey	Chrome leather	Grey	500	7,8	1800	44,0	560	-20	100	-30	130	FX+FXS	50	90-120
3-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	2,8	135	4,0	30	-20	100	-30	130	FX+FXS	20	90-120
5-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	2,9	225	5,0	30	-20	100	-30	130	FX+FXS	30	90-120
7-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	3,2	315	8,0	60	-20	100	-30	130	FX+FXS	30	90-120
10-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	3,5	450	10,5	90	-20	100	-30	130	FX+FXS	40	90-120
15-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	3,9	675	15,0	125	-20	100	-30	130	FX+FXS	45	90-120
20-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	4,6	900	22,0	280	-20	100	-30	130	FX+FXS	50	90-120
30-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	5,7	1350	33,0	320	-20	100	-30	130	FX+FXS	50	90-120
40-CLG	Rubber Smooth	Grey	Chrome leather	Grey	500	6,7	1800	44,0	560	-20	100	-30	130	FX+FXS	50	90-120